

测试报告

编号 : SZIN1805006789SC_CN

日期 : 2018-06-05

页码 : 1 of 4

客户名称: 深圳市铭朗纺织科技有限公司

客户地址: 深圳市平湖镇永华街 1 号 2 栋

样品名称 : 亚麻蜡线

产品规格 : M50

材质牌号 : 亚麻

以上信息及样品由客户提供及确认, SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性的责任。

SGS 参考号 : SL918092361251TX

收样日期 : 2018-05-24

测试开始时间 : 2018-05-24

测试结束时间 : 2018-06-05

测试结果 : 请见下页 (除另有特别说明外, 此报告结果仅对测试样品负责)

通标标准技术服务有限公司深圳分公司
检测中心
授权签名

熊娉婷

熊娉婷

授权签字人



测试报告

编号 : SZIN1805006789SC_CN

日期 : 2018-06-05

页码 : 2 of 4

测试结果:

要求

耐汗渍色牢度

(AATCC 15-2013)

酸性的

	(C)	
颜色变化	4.5	/
与多种纤维沾色		
醋酸纤维	4.5	/
棉	4.5	
尼龙	4.5	
涤纶	4.5	
晴纶	4.5	
羊毛	4.5	

摩擦色牢度

(AATCC 8-2016)

	(C)	
干擦	4.5	/
湿擦	4.5	/

备注: 灰卡评级为 1 至 5 级, 1 级为最差, 5 级为最好。

要求



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS Bldg, No. 4, Jianghao Industrial Park, No. 430, Jihua Road, Bantian, Longgang District, Shenzhen, China 518129 t (86-755) 25328282 f (86-755) 83197625 www.sgsgroup.com.cn
中国·深圳·龙岗区坂田吉华路430号江灏工业园4栋SGS大楼 邮编: 518129 t (86-755) 25328282 f (86-755) 83197625 e sgs.china@sgs.com

测试报告

编号 : SZIN1805006789SC_CN



日期 : 2018-06-05

页码 : 3 of 4

单纱强力(ASTM D2256/D2256M-10(R2015))

		(A)	(B)	(C)	(D)	
断裂强力	(lbf)	5.45	10.2	11.8	17.0	/
断裂伸长率	(%)	7.03	7.12	7.11	8.40	/

样品照片



	
M30(0.35MM)	M40(0.45MM)

测试报告

编号 : SZIN1805006789SC_CN

日期 : 2018-06-05

页码 : 4 of 4

	
M50(0.55MM)	M60(0.65MM)

附录信息:

1. 以上项目是在通标准技术服务有限公司广州分公司进行。
2. 该检测报告为由 SGS（深圳）发布的原检测报告编号：SZIN1805006789SC 的中文译本，如中英文有歧义，概以英文为准。

***** 报告结束*****